

**DEPARTMENT OF TRANSPORTATION
STATE OF GEORGIA**

SUPPLEMENTAL SPECIFICATION

Section 801—Fine Aggregate

Delete Subsection 801.2.02.A.7 and substitute the following:

7. Grades

Grade fine aggregates for Portland cement concrete and mortar as follows:

Size No.	Description	Total Percent by Weight Passing Each Sieve					
		3/ 8 in (9.5 mm)	No. 4 (4.75 mm)	No. 16 (1.18 mm)	No. 50 (300 µm)	No. 100 (150 µm)	No. 200 (75 µm)
10 NS	Natural concrete sand	100	95-100	45-95	5-30	0-10	0-3
20 NS	Natural mortar sand	100	100	90-100	15-50	0-15	0-5
10 SM	Standard manufactured concrete sand	100	95-100	45-95	8-30	1-10	0-4
10 FM	Fine manufactured concrete sand	100	95-100	45-95	15-42	6-22	0-9

Office of Materials and Testing