

November 17, 2006
Revised: May 30, 2012
Revised: November 16, 2012
July 10, 2013
February 27, 2014

**DEPARTMENT OF TRANSPORTATION
STATE OF GEORGIA**

SUPPLEMENTAL SPECIFICATION

Section 812—Backfill Materials

Delete Section 812 and substitute the following:

812.1 General Description

This section includes the requirements for four types of material used as backfill: foundation backfill, Types I and II, imperfect trench backfill, Type III, and mechanically stabilized wall backfill.

812.1.01 Related References

A. Standard Specifications

Section 810—Roadway Materials

B. Referenced Documents

AASHTO T 11

AASHTO T 27

AASHTO T 96

AASHTO T 104

GDT 4

GDT 6

GDT 7

GDT 24a

GDT 24b

GDT 67

GDT 75

GDT 98

SOP 1

812.2 Materials

812.2.01 Foundation Backfill, Type I

A. Requirements

1. Use natural or artificial mixtures of materials consisting of hard, durable particles of sand or stone, mixed with silt, clay and/or humus material for Type I backfill.
2. Have the final blend of material meet the requirements of Class I or II soils in Subsection 810.2.01.

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test as follows:

Test	Method
Soil gradation	GDT 4
Volume change	GDT 6
Maximum density	GDT 7 or GDT 67

D. Materials Warranty

General Provisions 101 through 150.

812.2.02 Foundation Backfill, Type II

A. Requirements

1. Type

Use material meeting the requirements of Section 800, Class A or B aggregate, and SOP 1. Crushed concrete may be used provided it meets the requirements of Section 800 that are applicable to Group 2 Aggregates.

Do not use backfill aggregate containing soil or decomposed rock.

2. Gradation

Use material meeting the following gradation requirements:

Sieve Size	% Passing by Weight
1-1/2 in (37.5 mm)	100
1 in (25 mm)	80-100
No. 8 (2.36 mm)	0-5

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test as follows:

Test	Method
Sieve analysis	AASHTO T 27

D. Materials Warranty

General Provisions 101 through 150.

812.2.03 Imperfect Trench Backfill, Type III

A. Requirements

1. Type

Use material made from either of the following for Type III backfill:

- A natural soil with a density of less than 95 lb/ft³ (1520 kg/m³) when tested with GDT 7
- An artificial mixture of soil and organic material, such as hay, leaves, or straw

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

The laboratory will:

1. Test the soil density with GDT 7.
2. Review the mixture and the percentages of each material, and approve a mixture suitable for the Project.

D. Materials Warranty

General Provisions 101 through 150.

812.2.04 Mechanically Stabilized Embankment Backfill

A. Requirements

Use material comprised of crushed stone, natural sand, or a blend of crushed stone and natural sand free of soils, organic or any other deleterious substances meeting the following additional requirements:

1. Crushed Stone

Use a material manufactured from Class A or B stone that is free of soil overburden, has a soundness loss of not more than 15 percent, and conforms to the requirements of SOP 1.

2. Natural Sand

May be used in conjunction with an approved, non-corrodible, extensible reinforcement. Use non-plastic material consisting of strong, hard, durable particles having a durability index of at least 70.

3. Gradation

Sieve Size	% Passing by Weight
4 in (100 mm)	100
2 in (50 mm)	80 -100
No. 10 (2 mm)	20 - 90*
No 200 (75 μm)	0 - 12
* Natural Sand may be 20 - 100	

4. Chemical

Ensure the material meets the following chemical requirements:

Test Method	Requirement
-------------	-------------

pH	*5.0 – 9.5
Resistivity	>3000 ohms/cm
Chlorides	<100 ppm
Sulfates	<200 ppm
Note: These chemical requirements are not applicable to MSE walls stabilized with an approved, non-corrodible, extensible reinforcement.	

*Sources of select backfill material having a pH between 4.5 and 5.0 may be used provided the interior face of the MSE wall panels have 3 inches of concrete cover over the reinforcement and the concrete used in the panels contains the following ingredients and proportions:

Material	% by Weight	
	Minimum	Maximum
Cement	30	--
Type F Fly Ash	10	20
Slag	50	60
Type F Fly Ash and Slag	--	70

5. Maximum Dry Density

Use backfill material with a maximum dry density equal to or greater than the design unit weight shown on the plans. If no maximum dry density of the backfill material is shown, use a weight of 125 lb/ft³ (2000 kg/m³).

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test the material as follows:

Test Method	Requirement
Percent Wear	AASHTO T96 ("A" Grading)
Sieve Analysis	AASHTO T 27
Material Passing No. 200 (75 μm) Sieve	AASHTO T 11
Durability Index	GDT 75
Maximum Dry Density	GDT 7 or GDT 24a, GDT 24b
Soundness (Magnesium Sulfate)	AASHTO T 104
pH	GDT 98
Resistivity	GDT 98
Chlorides	GDT 98
Sulfates	GDT 98

D. Materials Warranty